


RADICI PIETRO INDUSTRIES & BRANDS S.p.A.



NEXUS LINEA



Costruzione	Technique de fabrication	Construction	Herstellungsverfahren
Tufting velluto 5/64"	Tufted velours 5/64"	Tufted cut pile 5/64"	Getufted Velours 5/64"
Composizione 100% poliammide 6.6	Composition du velours 100% polyamide 6.6	Pile composition 100% polyamid 6.6	Polnutzschicht 100% polyamid 6.6
Sottofondo Juta sintetica	Dossier Jute synthétique	Secondary backing Synthetic jute	Rückenausüstung SDR Textilrucken
Punti al m² ± 320000	Touffes au m² ± 320000	Stitches per m² ± 320000	Knoten m² ± 320000
Altezza pelo ± 5.5 mm	Hauteur du velours ± 5.5 mm	Pile height ± 5.5 mm	Polhöhe ± 5.5 mm
Altezza totale ± 8 mm	Hauteur totale ± 8 mm	Total height ± 8 mm	Gesamtdicke ± 8 mm
Peso della fibra ± 640 g/m ²	Poids du velours ± 640 g/m ²	Yarn weight ± 640 g/m ²	Polgewicht ± 640 g/m ²
Peso totale ± 1750 g/m ²	Poids total ± 1750 g/m ²	Total weight ± 1750 g/m ²	Gesamtgewicht ± 1750 g/m ²
Larghezza rotolo 400 cm	Largeur du rouleau 400 cm	Roll width 400 cm	Breite 400 cm
Famiglia Tufting 1	Famiglia Tufting 1	Famiglia Tufting 1	Famiglia Tufting 1



Colour fastness to light	≥ 5 (4 pastel shade)	Thermal resistance m ² K/W	≤ 0,17
Insulation impact noise ΔLw	26 dB	Body voltage walking test kV	≤ 2
Acoustical absorption α _w	0,20		

RESISTENZA – WEARABILITY RESISTANCE - STRAPAZIERWERT				COMFORT – COMFORT CONFORT - KOMFORTWERT			
estrema extreme extrême extrem	elevata high élevée stark	normale good normale normal	sufficiente normal suffisante gering	medio medium moyen einfach	buono good bon gut	alto very good élevé hoch	ottimo excellent excellent luxuriös

Approved by Technique Management: M. Medica

Date: 12/11/2012