



RADICI PIETRO INDUSTRIES & BRANDS S.p.A.



VERONA



Specification in according EN 1307

| Costruzione | Technique de fabrication | Construction | Herstellungsverfahren |
|---|---|---|--|
| Tufting velluto cross-over 1/10" | Tufted velours cross-over 1/10" | Tufted cut pile cross-over 1/10" | Getufted Velours cross-over 1/10" |
| Composizione 75% poliammide 6.6 25% poliammide 6 | Composition du velours 75% polyamide 6.6 25% polyamide 6 | Pile composition 75% polyamid 6.6 25% polyamid 6 | Polnutschicht 75% polyamid 6.6 25% polyamid 6 |
| Sottofondo Juta sintetica | Dossier Jute synthétique | Secondary backing Synthetic jute | Rückenausrüstung SDR Textilrucken |
| Punti al m² ± 193550 | Touffes au m² ± 193550 | Stitches per m² ± 193550 | Knoten m² ± 193550 |
| Altezza pelo ± 5.7 mm | Hauteur du velours ± 5.7 mm | Pile height ± 5.7 mm | Polhöhe ± 5.7 mm |
| Altezza totale ± 8.2 mm | Hauteur totale ± 8.2 mm | Total height ± 8.2 mm | Gesamtdicke ± 8.2 mm |
| Peso della fibra ± 880 g/m ² | Poids du velours ± 880 g/m ² | Yarn weight ± 880 g/m ² | Polgewicht ± 880 g/m ² |
| Peso totale ± 1900 g/m ² | Poids total ± 1900 g/m ² | Total weight ± 1900 g/m ² | Gesamtgewicht ± 1900 g/m ² |
| Larghezza rotolo 400 cm | Largeur du rouleau 400 cm | Roll width 400 cm | Breite 400 cm |
| Famiglia Tufting 1 | Famiglia Tufting 1 | Famiglia Tufting 1 | Famiglia Tufting 1 |



U3P3E1C0
n°04/074



| | | | |
|--------------------------------------|----------------------|---------------------------------------|--------|
| Colour fastness to light | ≥ 5 (4 pastel shade) | Thermal resistance m ² K/W | ≤ 0,17 |
| Insulation impact noise ΔLw | 25 dB | Body voltage walking test kV | ≤ 2 |
| Acoustical absorption α _w | 0,25 | | |

| RESISTENZA – WEARABILITY RESISTANCE - STRAPAZIERWERT | | | | COMFORT – COMFORT CONFORT - KOMFORTWERT | | | |
|---|------------------------------------|--------------------------------------|---|--|-----------------------------|------------------------------------|--|
| estrema extreme extrême extrem | elevata high élevée stark | normale good normale normal | sufficiente normal suffisante gering | medio medium moyen einfach | buono good bon gut | alto very good élevé hoch | ottimo excellent excellent luxuriös |

Approved by Technique Management: M. Medica

Date: 26/11/2013